

Product: Ceramic Random Packing

Ceramic Pall Ring

Technical Data:

Spec.	D*H*T(mm)	Surface area (m ² /m ³)	Free volume (%)	Number per m ³	Bulk density (Kg/m ³)	Dry Packing Factor(m-1)
Ø 25	25*25*3	220	73	54000	620	565
Ø 38	38*38*4	150	75	13400	570	356
Ø 50	50*50*5	120	78	6800	550	252
Ø 80	80*80*8	75	80	1950	520	146

Physical properties

Index	Value
Specific gravity(g/cm ³)	2.25-2.35
Water absorption (%)	<0.5
Acid-resisting strength, %Wt. Loss (ASTMc279)	<4
Firing temperature(Degree C)	1280-1320
Softening point(Degree C)	>1400
Density(kg/m ³)	2350