

Product: Plastic Random Packing

Plastic VSP Inner Arc Ring

Product specification

Specification	D×H×T	Specific Area	Void ratio	Number	Bulk Density	Drying Packing Factor
mm	mm	m ² /m ³	m ³ /m ³	n/m ³	kg/m ³	m-1
φ25	25×12.5×1.2	250	0.93	81000	90	310
φ38	38×19×1.4	138	0.95	26800	78	163
φ50	50×25×1.5	121	0.95	10560	76	144
φ76	76×38×2.5	75	0.95	3400	70	86

Materials Physical Property

Performance/Material	PE	PP	RPP	PVC	CPVC	PVDF
Density (g/cm ³)	0.94-0.96	0.89-0.91	0.93-0.94	1.32-1.44	1.50-1.54	1.75-1.78
Operation Temp. (Centigrade)	90	>100	>120	>60	>90	>150
Chemical corrosion resistance	Good	Good	Good	Good	Good	Good
Compression Strength (Mpa)	>6.0	>6.5	>7.0	>6.0	>8.0	>10.0